High Performance Construction Joint Sealing



Revision: 3.0 - 09 October 2025 Code: HS-MF

INTRODUCTION

<u>Newton HydroCoat Monoflex</u> is a high performance joint-sealing system for construction, movement and expansion joints. It is particularly suitable in critical areas where irregular, high and/or frequent movement might be expected, as it is able to accommodate the movement whilst maintaining the waterproof seal over the joint.

The system consists of the HydroCoat Monoflex waterproofing tape, manufactured from a flexible polyolefine (FPO) which is installed to the substrate with the suitable Newton HydroCoat Monoflex Adhesive.

KEY BENEFITS

- Waterproofs construction joints that are subject to extreme movement
- Easy and quick to install and repair
- Excellent adhesion to different substrates with HydroCoat Monoflex Adhesive
- Resistant to 4 bar of water pressure to both the possitive and negative side
- Applied to both dry and damp concrete



Sealing of construction joints, movement joints, pipe penetrations, and cracks in all types of below-ground and water-retaining structures, such as:

- Basements
- Tunnels, culverts and hydroelectric plants
- Swimming pools
- Sewage and water treatment plants

SPECIFICATION


Newton Waterproofing Systems work in partnership with RIBA NBS and <u>NBS Source</u>, which integrates into project workflows, providing all product data from Newton's NBS BIM Objects, NBS Plus Clauses and RIBA Product Selector into one single source of product information.

NBS Source also hosts a large selection of Newton <u>case</u> <u>studies</u>, as well as product <u>literature and certifications</u>. A wide range of drawings are available <u>on our website</u>.

TRAINING AND COMPETENCY OF THE USER

Newton HydroCoat Monoflex should be installed by those with an understanding of the requirement to waterproof retained structures and the knowledge and training to use the product as part of a coordinated approach to the waterproofing of the structure, which in many cases will require further waterproofing products so as to achieve the required habitable grade as defined by BS 8102:2022.

Newton Specialist Contractors (NSBCs) are trained by Newton Waterproofing Systems in the correct specification and installation of Newton waterproofing products and will provide the client with a meaningful insurance backed guarantee for the waterproofing.



PURCHASE CODES

Product
 HydroCoat Monoflex - 100mm
 HydroCoat Monoflex - 200mm
 HydroCoat Monoflex Adhesive

HS-MF-200
HS-MFA

REQUIRED ANCILLARIES

Newton HydroCoat Monoflex Adhesive - 5 litres Two component, versatile and solvent-free epoxy
adhesive for installing HydroCoat Monoflex over the
joint/crack in the substrate. The adhesive is easy to
mix and apply on site, and exhibits excellent bond
strength even under damp conditions

PACKAGING

Newton HydroCoat Monoflex is supplied in 20m long rolls x widths of either 100mm or 200mm.

Newton HydroCoat Monoflex Adhesive is supplied in two containers with a combined volume of 5 litres.

SPECIALIST TOOLS REQUIRED

No specialist tools needed.

COLOUR

Grey

High Performance Construction Joint Sealing

TECHNICAL DATA				
Performance	HydroCoat Monoflex		Units	
Colour	Grey			
Material	Flexible polyolefine			
Width	100 / 200		mm	
Length	20		m	
Area	2/4		m²	
Thickness	1.0		mm	
Weight	930		g/m²	
Packaged weight	1.86 / 3.72		kg	
Shelf life	12		Months	
Resistance to temperature - min/max	-30 to +90		°C	
Installed Performance	Result	Units	Test Method	
Minimum joint width - as a percentage of tape width	0	%		
Maximum joint width - as a percentage of tape width	35	%		
Tear resistance - Lengthwise	15	N/mm²	DIN EN 12311-2 (Version B)	
Tear resistance - Across	15	N/mm²	DIN EN 12311-2 (Version B)	
Elongation at break - Lengthwise	620	%	DIN EN 12311-2 (Version B)	
Elongation at break - Across	670	%	DIN EN 12311-2 (Version B)	
Tear resistance (nail shank) - Lengthwise	260	N	DIN EN 12310-1	
Tear resistance (nail shank) - Across	260	N	DIN EN 12310-1	
Water vapour permeability	60	m	DIN EN 1931 (Version B)	
UV-Resistance min.	≥ 6500	h	DIN EN ISO 4892-3	
Shore A hardness	Approx. 87			
Bonding strength	≥ 4.0*	N/mm²	DIN EN 1348	
Peel test on wood carrier	≥ 100*	N		
Water tightness - 60 kPa/24 Std	Watertight		DIN EN 1928-A	
Water tightness - 400 kPa/72 Std	Watertight		DIN EN 1928-B	
Burst pressure	≥ 4.0	bar		
Reaction to fire	Class E		DIN ISO 11925-2 & EN 13501-1	

The above data, even if carried out according to regulated tests are indicative and they may change when specific site conditions vary. *Dependent on the adhesive used.


APPLICATION

- Ensure that the joint width is not more than 35% of the tape width. For example, the 100 mm wide tape will accommodate a 35 mm joint width.
- Where high levels of dynamic movement are expected, include an omega loop (slack) to allow some movement before the tape is tensioned. This will increase the service life of the joint.
- Use a brush or roller (depending on the substrate) to apply HydroCoat Monoflex Adhesive either side of the joint or crack to be sealed.
- Do not seal the central area immediately next to the joint/crack with adhesive - this section should not be adhered as it is important to allow the HydroCoat Monoflex to stretch with the substrate movement.



High Performance Construction Joint Sealing

- Lay the HydroCoat Monoflex onto the adhesive and press it in, avoiding creases and wrinkles in the material as much as possible.
- Smooth the HydroCoat Monoflex and push the adhesive outwards from the middle of the joint, maintaining the dry 'stretch zone' in the middle
- For overlaps between the ends of adjoining lengths of HydroCoat Monoflex, ensure that there is a 10cm overlap and roughen the overlapping sections with sandpaper (80 grit).







 If the HydroCoat Monoflex is not to be covered or protected, apply another layer of adhesive on top, leaving an area of 20 - 30mm directly above the joint/ crack free from adhesive



STORAGE

It is essential that goods are kept in the original packaging, keep cool and dry, protect against sunlight.

If packaging film has been opened then apply the material within 2 months.

HEALTH AND SAFETY

Use appropriate PPE for the environment the system is installed within. Use products only as stated within this Data Sheet and the Safety Data Sheet.

High Performance Construction Joint Sealing





Newton Waterproofing Systems Newton House 17-19 Sovereign Way Tonbridge Kent TN9 1RH

JST-O Monoflex 1mm DIN EN 13967

Synthetic waterproofing membrane cosists of flexible Polyolefine (FPO) according to DIN-EN 13967 for waterproofing of buildings.

		waterproofing of buildings.	
Essential characteristics to DIN EN 139	67 Performance	Harmonised Technical Specification	
Length	-0 m / +0.2 m		
Width	± 2 mm		
Thickness (waterproofing membrane)	1 mm ± 0.1 mm		
Straightness	Passed		
Mass per unit area	$x = 930 \text{ g/m}^2 \pm 50 \text{ g/m}^2$		
Visible defects	Free of visible defects		
Water tightness - 60kPa / 24h Water tightness - 400kPa / 72h	Passed Passed		
Resistance to impact A: Alu plate Resistance to impact B: EPS panel	≤ 250 mm ≤ 1500 mm		
Durability of water tightness against thermal ageing	Passed	DIN EN 13967	
Durability of water tightness against chemicals	Passed		
Compatibility with bitumen Water tightness	Passed	BIN EN 13307	
Tear resistance (Nail shank)	Longitudinal: ≥ 200 N Lateral: ≥ 200 N		
Shear resistance of the joint seams	≥ 300 N / 50 mm		
Water vapour permeability - SD-Value	g = $6.80 \cdot 10^{-9}$ kg / (m ² s) ± 30% 60 m ± 20 m		
Resistance to static loads Method A: EPS panel Resistance to static loads Method B: Substrate concre	≥ 20 kg ≥ 20 kg		
Tensile properties	Longitudinal: ≥ 12.5 N/mm ² Lateral: ≥ 12.5 N/mm ² Longitudinal: ≥ 500% Lateral: ≥ 500%		
Reaction to fire	Class E		

Newton Waterproofing Systems reserve the right to update product literature at any time. Please always refer to our website for the latest versions.